

System sheet PA-BBS T 35

Description


Waterproofing based on Rocathaan Hotspray with Rocathaan topcoating.

Application area's

- Grandstands
- Flooring
- Walkways
- Roofing
- Galleries

Most important properties

- Seamless
- Crack bridging
- Abrasion resistant
- Elastic



1. Pre-treat surface correctly
2. Rocapox Resin 100 ($\pm 0,30 \text{ kg/m}^2/\text{layer}$)
3. Rocapox Screed ($\pm 1 \text{ kg/m}^2/\text{layer}$)
4. Rocathaan Hotspray PA 136-T ($\pm 2,5 \text{ kg/m}^2/\text{layer}$)
5. First layer of Rocathaan Topcoat 35 ($\pm 0,15 \text{ kg/m}^2/\text{layer}$)
6. Second layer of Rocathaan Topcoat 35 ($\pm 0,15 \text{ kg/m}^2/\text{layer}$)

Check before application the datasheets. If necessary, contact your technical advisor.

The stated consumption figures are indicative and based on smooth, flat surfaces. The actual consumption depends on the application method, roughness and absorbency of the substrate.

The information and consumption per layer are indicative.



Tel. +31 (0)85 78 200 20 • Fax. +31 (0)85 78 200 21
www.prokol.com • info@prokol.com

Liquid synthetic materials for a sustainable future